



Temperature in [°C]: **20.0** **-40.0** **100.0** **150.0** **200.0**

magnetic properties					
Remanence 20°C	Br min	0.360	T	3.6	kG
	Br nom	0.375	T	3.8	kG
Coercivity 20°C	HcB min	222	kA/m	2.8	kOe
	HcB nom	239	kA/m	3.0	kOe
Intrinsic Coercivity 20°C	HcJ min	238	kA/m	3.0	kOe
	HcJ nom	262	kA/m	3.3	kOe
Maximum Energy Product 20°C	BH max, min	24	kJ/m ³	3.0	MGOe
	BH max, nom	26	kJ/m ³	3.3	MGOe
Reversible Temperature Coefficient ¹⁾	α Br nom	-0.200	%/°C		
	β HcJ nom	0.300	%/°C		

material properties (typical values)					
Max. Operating Temperature ²⁾	T max	250	°C		
Density	ρ	4.95	g/cm ³		
Permeability 20°C	μr	1.1			
Vickers Hardness		500-600	HV		
Modulus of Elasticity	E	15 - 200	kN/mm ²		
Copressive Strength		600 - 700	N/mm ²		
Flexural Strength		55	N/mm ²		
Expansion Coefficient		-	10 ⁻⁶ /K		
Expansion Coefficient in direction of anisotropy	⊥	10.0 - 11.0	10 ⁻⁶ /K		
	//	12.0 - 13.0	10 ⁻⁶ /K		
Specific Electric Resistance	ρel	1000000000	μΩ m		
Specific Heat Capacity	c	700	J/(kg K)		
Thermal Conductivity	λ	4	W/m K		

1) The shown temperature coefficients are nominal reference values only . They can vary for different temperatures and don't need to be linear.

2) The maximum operating temperature is depending on the magnet shape, size and on the specific application.

Note: The above plotted graphs are idealized and represent theoretical values of the material. Shown are curves according nominal values based on uncoated material samples according to IEC 60404-5. Material and magnetic data represent typical data that may vary due to product shape, size and coating. Please contact Bomatec regarding specific requirements for your application.