



Temperature in [°C]: **20.0** **80.0** **100.0** **125.0**

magnetic properties

Remanence 20°C	Br min	0.670	T	6.7	kG
	Br nom	0.680	T	6.8	kG
Coercivity 20°C	HcB min	453	kA/m	5.7	kOe
	HcB nom	483	kA/m	6.1	kOe
Intrinsic Coercivity 20°C	HcJ min	867	kA/m	10.9	kOe
	HcJ nom	911	kA/m	11.4	kOe
Maximum Energy Product 20°C	BH max, min	82	kJ/m ³	10.3	MGOe
	BH max, nom	85.95	kJ/m ³	10.8	MGOe
Reversible Temperature Coefficient ¹⁾	α Br nom	-0.040	%/°C		
	β HcJ nom	-0.200	%/°C		

material properties (typical values)

Max. Operating Temperature ²⁾	T max	125	°C		
Density	ρ	5.95	g/cm ³		
Permeability 20°C	μr	1.05			
Flexural Strength		ca. 75	Mpa		

1) The shown temperature coefficients are nominal reference values only . They can vary for different temperatures and don't need to be linear.
 2) The maximum operating temperature is depending on the magnet shape, size and on the specific application.

Note: The above plotted graphs are idealized and represent theoretical values of the material. Shown are curves according nominal values based on uncoated material samples according to IEC 60404-5. Material and magnetic data represent typical data that may vary due to product shape, size and coating. Please contact Bomatec regarding specific requirements for your application.