



Temperature in [°C]: **20.0** **80.0** **100.0** **150.0** **200.0** **250.0**

magnetic properties

Remanence 20°C	Br min	1.100	T	11.0	kG
	Br nom	1.125	T	11.3	kG
Coercivity 20°C	HcB min	540	kA/m	6.8	kOe
	HcB nom	675	kA/m	8.5	kOe
Intrinsic Coercivity 20°C	HcJ min	635	kA/m	8.0	kOe
	HcJ nom	795	kA/m	10.0	kOe
Maximum Energy Product 20°C	BH max, min	230	kJ/m ³	28.9	MGOe
	BH max, nom	242.5	kJ/m ³	30.5	MGOe
Reversible Temperature Coefficient ¹⁾	α Br nom	-0.035	%/°C		
	β HcJ nom	-0.200	%/°C		

material properties (typical values)

Max. Operating Temperature ²⁾	T max	250	°C		
Density	ρ	8.4	g/cm ³		
Permeability 20°C	μr	1.1			
Vickers Hardness		575	HV		
Modulus of Elasticity	E	150	kN/mm ²		
Compressive Strength		700	N/mm ²		
Flexural Strength		120	N/mm ²		
Expansion Coefficient		-	10 ⁻⁶ /K		
Expansion Coefficient in direction of anisotropy	⊥	9-13	10 ⁻⁶ /K		
	//	6-10	10 ⁻⁶ /K		
Specific Electric Resistance	ρel	0.7-1.1	μΩ m		
Specific Heat Capacity	c	370	J/(kg K)		
Thermal Conductivity	λ	10.0 - 13.0	W/mK		

1) The shown temperature coefficients are nominal reference values only. They can vary for different temperatures and don't need to be linear.

2) The maximum operating temperature is depending on the magnet shape, size and on the specific application.

Note: The above plotted graphs are idealized and represent theoretical values of the material. Shown are curves according nominal values based on uncoated material samples according to IEC 60404-5. Material and magnetic data represent typical data that may vary due to product shape, size and coating. Please contact Bomatec regarding specific requirements for your application.